DuPont™ Delrin® SC631 NC010 ACETAL RESIN

Product Information

Common features of Delrin® acetal resins include mechanical and physical properties such as high mechanical strength and rigidity, excellent fatigue and impact resistance, as well as resistance to moisture, gasoline, lubricants, solvents, and many other neutral chemicals. Delrin® acetal resins also have excellent dimensional stability and good electrical insulating characteristics. They are naturally resilient, self-lubricating, and available in a variety of colors and speciality grades.

Delrin® acetal resin typically is used in demanding applications in the automotive, domestic appliances, sports, industrial engineering, electronics, and consumer goods industries.

Delrin® SC631 is a medium-high viscosity acetal homopolymer, developed for parts requiring high precision molding in the healthcare industry.

SPECIAL CONTROL for HEALTHCARE APPLICATIONS

This product is manufactured according to Good Manufacturing Practice (GMP) principles and generally accepted in food contact applications in Europe and the USA when meeting applicable use conditions. This product is also tested against ISO 10993-5 and -11 and selected parts of USP Class VI. For details, individual compliance statements are available from your DuPont representative.

The below datasheet is a condensed version. For a complete datasheet, please contact your DuPont representative.

General information	Value	Unit	Test Standard
Resin Identification	POM	-	ISO 1043
Part Marking Code	POM	-	ISO 11469
Mechanical properties	Value	Unit	Test Standard
Tensile Modulus	3300	MPa	ISO 527-1/-2
Yield stress	74	MPa	ISO 527-1/-2
Yield strain	15	%	ISO 527-1/-2
Nominal strain at break	35	%	ISO 527-1/-2
Charpy notched impact strength, 73°F	9	kJ/m²	ISO 179/1eA
Thermal properties	Value	Unit	Test Standard
Melting temperature, 18°F/min	178	°C	ISO 11357-1/-3
Other properties	Value	Unit	Test Standard
Density	1420	kg/m³	ISO 1183
VDA Properties	Value	Unit	Test Standard
Emissions	<8	mg/kg	VDA 275
Fogging, G-value (condensate)	0.4	mg	ISO 6452
Chausatauistiaa			

Characteristics					
Processing	 Injection Molding 				
Delivery form	 Pellets 				
Additives	 Lubricants 	Release agent			
Regional Availability	North AmericaEurope	Asia PacificSouth and Central America	Near East/AfricaGlobal		

Contact DuPont for Material Safety Data Sheet, general guides and/or additional information about ventilation, handling, purging, drying, etc. ISO Mechanical properties measured at 160 mil (Hytrel® measured at 80 mil), IEC Electrical properties measured at 80 mil, all ASTM properties measured at 120 mil, and test temperatures are 73°F unless otherwise stated.

The information set forth herein is furnished free of charge and is based on technical data that DuPont believes to be reliable and falls within the normal range of properties. It is intended for use by persons having technical skill, at their own discretion and risk. This data should not be used to establish specification limits nor used alone as the basis of design. Handling precaution information is given with the understanding that those using it will satisfy themselves that their particular conditions of use present no health or safety hazards. Since conditions of product use and disposal are outside our control, we make no warranties, express or implied, and assume no liability in connection with any use of this information. As with any product, evaluation under end-use conditions prior to specification is essential. Nothing herein is to be taken as a license to operate or a recommendation to infringe on patents. Caution: Do not use in medical applications involving permanent implantation in the human body. For other medical applications, discuss with your DuPont customer representative and read Medical Caution H-50103-5.

Copyright © 2017 DuPont or its affiliates. All Rights Reserved. The DuPont Oval Logo, DuPont™, The miracles of science™ and all products

Revised: 2017-01-19

To find out more, visit DuPont Performance Polymers or contact nearest DuPont location.

 North America
 Asia Pacific
 Europe/Middle East/Africa

 Tel: +1 302 999-4592
 Tel: +81 3 5521 8600
 Tel: +41 22 717 51 11

Toll-Free (USA): 800 441-0575

Copyright 2017 DuPont. The DuPont Oval Logo is a trademark or registered trademark of E.I. du Pont de Nemours and Company or its affiliates. All rights reserved.



Page: 1 of 2

DuPont™ Delrin® SC631 NC010 **ACETAL RESIN**

denoted with ® or ™ are registered trademarks or trademarks of E.I. du Pont de Nemours and Company or its affiliates.

Revised: 2017-01-19 Page: 2 of 2

To find out more, visit DuPont Performance Polymers or contact nearest DuPont location.

North America

Asia Pacific Tel: +81 3 5521 8600 Tel: +1 302 999-4592

Europe/Middle East/Africa

Tel: +41 22 717 51 11

