

Grilamid LV-3 X ESD black PA12-GF30

EMS-GRIVORY | a unit of EMS-CHEMIE AG

Product Texts

Product designation according to ISO 1874:

PA 12, MHRZ, 18-080, GF30+C

Max. usage temperature (short term)

Mechanical properties	dry / cond	Unit	Test Standard
Tensile Modulus	7500 / 7100	MPa	ISO 527-1/-2
Stress at break	130 / 120	MPa	ISO 527-1/-2
Strain at break	4.5 / 4.5	%	ISO 527-1/-2
Charpy impact strength (+23°C)	75 / 60	kJ/m²	ISO 179/1eU
Charpy impact strength (-30°C)	- / 45	kJ/m²	ISO 179/1eU
Charpy notched impact strength (+23°C)	11 / 11	kJ/m²	ISO 179/1eA
Charpy notched impact strength (-30°C)	9/9	kJ/m²	ISO 179/1eA
Machanical association (TDF)	des / cond	I I to St	Took Chandond
Mechanical properties (TPE)	dry / cond	Unit	Test Standard
Ball indentation hardness	- / 125	MPa	ISO 2039-1

Thermal properties	dry / cond	Unit	Test Standard
Melting temperature (10°C/min)	178 / -	°C	ISO 11357-1/-3
Temp. of deflection under load (1.80 MPa)	165 / -	°C	ISO 75-1/-2
Temp. of deflection under load (8.00 MPa)	125 / -	°C	ISO 75-1/-2
Coeff. of linear therm. expansion (parallel)	80 / -	E-6/K	ISO 11359-1/-2
Coeff. of linear therm. expansion (normal)	120 / -	E-6/K	ISO 11359-1/-2
Burning Behav. at thickness h	HB / -	class	IEC 60695-11-10
Thickness tested	0.8 / -	mm	IEC 60695-11-10
Max. usage temperature (long term)	90 - 120	°C	ISO 2578

Electrical properties	dry / cond	Unit	Test Standard
Volume resistivity	- / 100	Ohm*m	IEC 60093
Surface resistivity	- / 1000	Ohm	IEC 60093

150

°C

EMS

Other properties	dry / cond	Unit	Test Standard
Water absorption	1/-	%	Sim. to ISO 62
Humidity absorption	0.5 / -	%	Sim. to ISO 62
Density	1290 / -	kg/m³	ISO 1183

Rheo/Phys properties	dry / cond	Unit	Test Standard
Molding shrinkage (parallel)	0.2 / -	%	ISO 294-4, 2577
Molding shrinkage (normal)	1.0 / -	%	ISO 294-4, 2577

Characteristics

Processing	Regional Availability
Injection Molding	North America, Europe, Asia Pacific, South and Central America, Near East/Africa
Delivery form	
Granules	Product Attributes
	Hydrolysis resistant
Special Characteristics	
Auti static I link import on import modified languaged IIV/ maistages	Automotive
Anti-static, High impact or impact modified, Improved UV resistance (outdoor use), Improved heat resistance	Fuel systems

Created: 2017-08-11 Source: www.materialdatacenter.com

Page: 1/1

The values are intended to serve as an aid in preselecting materials and for an overview of the EMS-GRIVORY product range. The information contained in this publication is based on our present knowledge and experience. The given figures and data are guidance values and do not represent binding material specifications. No warranties of any kind, either express or implied, including warranties of merchantability or fitness for a particular purpose, are given regarding products, design, data and information. The customer is not released from his obligation to investigate the products fitness and the suitability for the intended application, compliance with legal requirements and intellectual property rights. We reserve the right to change the information at any time and without prior notice. The information in this publication is not to be considered a contractual obligation and anyliability whatsoever is expressly declined. For further questions about our products please contact our experts.