

## POLYPLASTICS CO LTD

18-1 KONAN, 2-CHOME, MINATO-KU TOKYO 108-8280 JP



DURACON: M25-44(r5), M90-44(r5), M140-44(r5), M270-44(r5), M450-44(r5)

Acetal "Polyoxymethylene" (POM), pellets

(r5) - Virgin and Regrind from 1 to 100% by weight inclusive have the same basic material charactersitics except for the RTI's are 50C for all three properties for Regrind from 26 - 100%

| Flammability                          | Value           | Test Method          |
|---------------------------------------|-----------------|----------------------|
| Flame Rating                          |                 | UL 94                |
| 0.75 mm, ALL                          | HB              |                      |
| 1.5 mm, ALL                           | HB              |                      |
| 3.0 mm, ALL                           | HB              |                      |
| Flammability Classification           |                 | IEC 60695-11-10, -20 |
| 3.0 mm, ALL                           | HB40            |                      |
| 0.75 mm, ALL                          | HB75            |                      |
| 1.5 mm, ALL                           | HB75            |                      |
| Electrical                            | Value           | Test Method          |
| Hot-wire Ignition (HWI)               |                 | UL 746               |
| 0.75 mm                               | PLC 4           |                      |
| 1.5 mm                                | PLC 4           |                      |
| 3.0 mm                                | PLC 3           |                      |
| High Amp Arc Ignition (HAI)           |                 | UL 746               |
| 0.75 mm                               | PLC 0           |                      |
| 1.5 mm                                | PLC 0           |                      |
| 3.0 mm                                | PLC 0           |                      |
| Comparative Tracking Index (CTI)      | PLC 0           | UL 746               |
| Dielectric Strength                   | 29 kV/mm        | ASTM D149            |
| High Voltage Arc Tracking Rate (HVTR) | PLC 0           | UL 746               |
| Volume Resistivity                    | 1.0E+15 ohms·cm | ASTM D257            |
| Volume Resistivity                    | 1.0E+15 ohms·cm | IEC 60093            |
| Arc Resistance                        | PLC 5           | ASTM D495            |
| Electric Strength                     | 29 kV/mm        | IEC 60243-1          |
| Thermal                               | Value           | Test Method          |
| RTI Elec                              |                 | UL 746               |
| 0.75 mm                               | 110 °C          |                      |
| 1.5 mm                                | 110 °C          |                      |
| 3.0 mm                                | 110 °C          |                      |
| RTI Imp                               |                 | UL 746               |
| 0.75 mm                               | 95.0 °C         |                      |
| 1.5 mm                                | 95.0 °C         |                      |
| 3.0 mm                                | 95.0 °C         |                      |
| RTI Str                               |                 | UL 746               |
| 0.75 mm                               | 100°C           |                      |
| 1.5 mm                                | 100 °C          |                      |
| 3.0 mm                                | 100 °C          |                      |
| Physical                              | Value           | Test Method          |
| Dimensional Stability                 | 0.0 %           | ASTM D1042           |
|                                       |                 |                      |

UL and the UL logo are trademarks of UL LLC Copyright © 2017 All Rights Reserved. | www.ul.com

Page 1 of 2

Report Date: 6/5/1984 Last Revised: 2013-12-11

Form Number: E45034-100337529

## Component - Plastics

File Number: E45034



| Physical              | Value | Test Method |
|-----------------------|-------|-------------|
| Dimensional Stability | 0.0 % | ISO 2796    |
|                       |       |             |

## **Notice of Disclaimer**

By accessing this Yellow Card data information sheet and the database from which this information was generated (the "Yellow Card"), the user acknowledges and accepts the terms and conditions upon which this Yellow Card is made available. This Yellow Card, the database from which it was generated, and all related materials, support, and services, are made available by UL for use only by permission and "as is", without any representation or warranty of any kind, express or implied, including but not limited to any implied warranties of merchantability, fitness for a particular purpose or that the products identified in this Yellow Card will satisfy the user's requirements. UL cannot and does not warrant that the data contained in this Yellow Card is current, accurate, or complete. The user must independently confirm the conformance of any product to the applicable standards or requirements with the manufacturer of that product. Permission to access this Yellow Card may be withdrawn at any time by UL in its sole discretion. The identification of products and companies on this Yellow Card does not in any way imply endorsement of those products or companies by UL. UL does not assume and expressly disclaims, liability to any person for any loss or damage (including lost profits, lost savings, or any indirect, special, incidental, consequential or punitive damages whether or not UL has been advised of the possibility of such damages) arising out of, or in connection with, the use of this Yellow Card regardless of the cause or causes of such loss or damage.